



GUTEX Thermofibre

TECHNICAL DATA SHEET



Blow-in bulk density ρ exposed [kg/m ³]	25 – 30
Blow-in bulk density ρ enclosed [kg/m ³]	29 – 50
Nominal thermal conductivity λ_D [W/mK]	0.038
Vapour diffusion μ	2
Air flow resistivity [kPa s/m ²]	≥ 3
Specific heat capacity [J/kgK]	2100
Fire reaction Euro Class as per EN 13501-1	E
Approval number	ETA-12/0181

GUTEX Thermofibre – ideal for compartments and as exposed insulation on horizontal surfaces.

Ingredients

- Untreated fir and spruce
- Flame retardant: 5.0 % ammonium salts

Disposal

- Waste code numbers as per AVV
030105, 170201





GUTEX Thermofibre

Detailed information

Version	Unpacked	Packed
Thickness [mm]	330	
Length × width [mm × mm]	400 × 800	
kg/Bale	15.00	
Bale/Pallet	18	21
Weight per pallet [kg]	290	330





GUTEX Thermofibre

PRODUCT INFORMATION

Areas of use

- Between studs in interior and exterior walls
- Between-rafter insulation
- Ceiling insulation
- Partition walls/dry construction
- Interior insulation

Advantages

- Elastic for adjustability
- Flexible in shape and variable in format
- Settling-resistant from 29 kg/m³
- High, consistent fibre quality
- Outstanding thermal insulation
- Outstanding specific heat capacity → protection from heat in summer and cold in winter
- Excellent sound insulation
- Easy and quick to work with
- Moisture-regulating
- Steam vapour-permeable
- Wood as the sustainable raw material → recyclable
- Ecologically safe (natureplus® certified)

